

Thermal Silicone Rubber CTLC300

CTLC300 thermal pad is a general-purpose and economical thermal conductive gap filler, cost-effective, soft and self-adhesive, easy to assemble. It shows good thermal conductivity and electrical insulation performance under low compression force. It is placed between the heating device and the gap between the heat sink or the machine shell, and the air is squeezed out to achieve full contact, forming a continuous heat conduction channel. Using the heat sink or the machine shell As a heat dissipation device, the heat dissipation area can be effectively increased, thereby effectively improving the heat dissipation effect.



Product Features

- Low cost, high efficiency and high cost performance.
- Thermal grease to replace volatile pollution.
- Natural stickiness, easy assembly, repeatable disassembly.
- Wide thickness range, can fill any uneven size gap.
- High electrical insulation.

Typical Applications

- Computer/communication equipment.
- Laptop / tablet / PC server.
- New energy power battery / vehicle equipment.
- Switching power supply / UPS.
- Video / security equipment.
- Any heating element and radiator.

Electrically Insulating, Thermally Conductive Elastomeric Material

TYPICAL PROPERTIES OF SILICONE RUBBER CTLC300

Test Item	Unit	CTLC300	Test Method
Colour	-	Blue	Visually
Thickness	mm	0.3~15	ASTM D374/374M
Hardness	Shore AO	30±5	GB/T531
	Shore OO	60±10	ASTM D2240
Specific Gravity	g/cm ³	3.07±0.2	ASTM D792
Tensile Strength	MPa	0.16	ASTM D412
Elongation at Break	%	90	ASTM D412
Breakdown Voltage	KV/mm	≥10	ASTM D149
Volume Resistivity	Ω·cm	≥1×10 ¹³	ASTM D257
Temp Resistance	°C	-40~200	-
Flame	-	V-0	UL 94
Weight Loss	%	≤0.3	@150°C 240H
Permittivity	@1MHz	6.04	ASTM D150
Thermal Conductivity	W/mk	3.0±0.3	ISO 22007-2
Thermal Conductivity	W/mk	3.0±0.3	ASTM D5470
Thermal Impedance	°C·in ² /W	0.586	ASTM D5470
Thermal Impedance	°C·cm ² /W	3.779	ASTM D5470
Specific Heat Capacity	J/g/k	0.952	ASTM E1269

Configurations Available:

- Sheet form, die-cut parts, and roll form
- With or without pressure sensitive adhesive

Build a Part Number

Standard Options

CTLC300 - H0060 - T10 - 50 - 100 - NA

- Your part/drawing No.
- Length = 100mm
- Width = 50mm
- Thickness = 1.0mm
- Hardness Shore OO 60
- CTLC300 with thermal conductivity 3.0w/mk

Note: The material can be customized. If you can't find the material that meets your requirements in our existing materials, you can consult the sales manager whether the material you need supports customization, and we will give you a reply within 24H.

www.coolthermo.com

CoolThermo - Asia

Phone: 86-133-1690-6731

Skype: 86-133-1690-6731

Email: info@coolthermo.com

Add: Room 101, No. 214, District 3, Longsheng New Village, Longsheng Community, Dalang Street, Longhua District, Shenzhen 518110

All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKETABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE A PRODUCT. No statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer.